

## **TAT-125**

## Raychem

# Flexible, adhesive-lined, polyolefin heat-shrinkable tubing

TAT-125 is an adhesive-lined, flexible, thin-wall, heat-shrinkable tubing. It provides one-step electrical insulation and moisture sealing for a wide variety of applications.

TAT-125 is especially suitable for applications where the moisture seal

must withstand flexing or other physical abuse. Because both tubing and adhesive are flexible, the moisture seal is resistant to bending of the substrate.

The thin adhesive lining of TAT-125 melts and flows with the heat of

application to form a positive environmental seal. The adhesive will adhere to a wide variety of plastics, rubbers, and metals, including PVC, polyethylene, neoprene, lead, and steel.

### Temperature rating


Full recovery temperature:	121°C
Continuous operating temperature:	−55°C to 110°C

#### Specifications\*

			.74	
Туре	Raychem	Military	UL	
TAT-125 Type 1 (colors)	RW-3032	AMS-DTL-23053/4, Cl. 2	E85381	
TAT-125 Type 2 (clear)	RW-3032			

<sup>\*</sup>When ordering, always specify latest issue.

#### Dimensions (millimeters/inches)



Inside diameter		Recovered wall thickness**	
D (min.)	d (max.)	W	W1
Expanded	Recovered	Nominal	Nominal
as supplied	after heating	total wall	adhesive wall
3.2 <i>0.125</i>	1.6 0.062	0.68 0.027	0.23 0.009
4.7 0.187	2.4 0.093	0.71 <i>0.028</i>	0.25 0.010
6.4 0.250	3.2 <i>0.125</i>	0.74 0.029	0.13 0.005
9.5 <i>0.375</i>	4.7 0.187	0.74 0.029	0.13 0.005
12.7 0.500	6.4 0.250	0.76 0.030	0.15 0.006
19.1 <i>0.750</i>	9.5 <i>0.375</i>	0.89 <i>0.035</i>	0.15 0.006
25.4 1.000	12.7 <i>0.500</i>	1.07 0.042	0.20 0.008
38.1 <i>1.500</i>	19.1 <i>0.750</i>	1.19 0.047	0.28 0.012
50.8 <i>2.000</i>	25.4 1.000	1.65 <i>0.065</i>	0.56 0.022
76.2 3.000	38.1 <i>1.500</i>	1.65 <i>0.065</i>	0.56 0.022
101.6 4.000	50.8 <i>2.000</i>	1.78 <i>0.070</i>	0.56 0.022
	D (min.) Expanded as supplied 3.2 0.125 4.7 0.187 6.4 0.250 9.5 0.375 12.7 0.500 19.1 0.750 25.4 1.000 38.1 1.500 50.8 2.000 76.2 3.000	D (min.)         d (max.)           Expanded as supplied         after heating           3.2 0.125         1.6 0.062           4.7 0.187         2.4 0.093           6.4 0.250         3.2 0.125           9.5 0.375         4.7 0.187           12.7 0.500         6.4 0.250           19.1 0.750         9.5 0.375           25.4 1.000         12.7 0.500           38.1 1.500         19.1 0.750           50.8 2.000         25.4 1.000           76.2 3.000         38.1 1.500	D (min.)         d (max.)         W           Expanded as supplied         Recovered         Nominal total wall           3.2 0.125         1.6 0.062         0.68 0.027           4.7 0.187         2.4 0.093         0.71 0.028           6.4 0.250         3.2 0.125         0.74 0.029           9.5 0.375         4.7 0.187         0.74 0.029           12.7 0.500         6.4 0.250         0.76 0.030           19.1 0.750         9.5 0.375         0.89 0.035           25.4 1.000         12.7 0.500         1.07 0.042           38.1 1.500         19.1 0.750         1.19 0.047           50.8 2.000         25.4 1.000         1.65 0.065           76.2 3.000         38.1 1.500         1.65 0.065

<sup>\*\*</sup>Wall thickness will be less if tubing recovery is restricted during shrinkage.

#### Ordering information

Standard	Black	
Nonstandard	White, red, blue, yellow, green, orange, brown, violet, clear (non-flame-retardant jacket)	
Always order the largest size that will shrink snugly over the component being covered.		
4-foot lengths		
Sizes of 2 inches and larger are by special order only. Other nonstandard sizes are available upon special request.		
Specify product name, size, and color: for example. TAT-125 1/4-0 (0=Black).		
	Nonstandard Always order the 4-foot lengths Sizes of 2 inches	

#### Specification values

	Property	Unit	Requirement	Method of test
Physical	Dimensions	mm (inches)	See reverse	ASTM D 2671
	Longitudinal change*	percent	+0, –5 maximum	ASTM D 2671
	Tensile strength	psi	1500 minimum	ASTM D 2671
	Ultimate elongation	percent	200 minimum	ASTM D 2671
	Secant modulus (as supplied)	psi	2.5 x 10 <sup>4</sup> maximum	ASTM D 2671
	Cold impact (at –55°C/–67°F)		No cracking	AMS-DTL-23053
	Heat shock (4 hours at 250°C/482°F)		No dripping, flowing, or cracking of outer wall	AMS-DTL-23053
	Heat resistance (168 hours at 175°C/347°F)		No dripping, flowing, or cracking of outer wall	AMS-DTL-23053
	Color		Pass	MIL-STD 104
	Color stability (24 hours at 175°C/347°F)		Pass	MIL-STD 104
Electrical	Dielectric strength Sizes 1/8" through 1"	volts/mil	500 minimum	ASTM D 2671
	Sizes 1/8" and larger		400 minimum	
	Volume resistivity	ohm-cm	1 X 10 <sup>12</sup> minimum	ASTM D 2671
Chemical	Copper corrosion (16 hours at 121°C/250°F)		No corrosion	ASTM D 2671 Procedures A & B
	Flame retardancy**		Self-extinguishing within 1 minute, 25% maximum flag burn	AMS-DTL-23053 Test A
	Fungus resistance		Rating of 1 or less	ASTM G21
	Water absorption (24 hours at 23°C/73°F)	percent	0.5 maximum	ASTM D 2671
	Fluid resistance (24 hours at 24°C/75°F) in: Hydraulic fluid (MIL-H-5606) JP-8 fuel (MIL-T-5624) Lubricating oil (MIL-L-7808 and MIL-I-23699) Salt water, 5% (O-S-1926) De-icing fluid (MIL-A-8243) Followed by tests for:		AMS-DTL-23053	
	Tensile strength	psi	1000 minimum	ASTM D 2671
	Dielectric strength	volts/mil	•	ASTM D 2671
	Sizes 1/8" through 1"		400 minimum	= ==
	Sizes 1 1/2" and larger		300 minimum	

Note: Except for dimensions and longitudinal change, specification values apply to outer jacket only. \*Sizes and colors not included in AMS-DTL-23053/4, Class 2 have a longitudinal change requirement of +0, -10 maximum. \*\*Only the outer jacket of TAT-125 is flame-retardant; the outer jacket of clear TAT-125, however, is not flame-retardant.

Typical properties	Adhesive		
	Peel strength		T-PEEL, 2"/minute
	Polyethylene	15 lb./in. width	
	Neoprene	10 lb./in. width	
	PVC	10 lb./in. width	
	Lead	5 lb./in. width	
	Steel	15 lb./in. width	

Raychem is a trademark of Tyco Electronics Corporation.

Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation

300 Constitution Drive Menlo Park, CA 94025-1164 USA

Tel: (800) 926-2425 (US & Canada) Tel: +1 (650) 361-3860 (All other countries) Faraday Road Dorcan, Swindon, SN3 5HH United Kingdom Tel: +44 1793 528171 3816 Noborito, Tama-ku Kawasaki, Kanagawa 214-8533 Japan Tel: +81 44 900 5102 Asia Pacific Headquarters 26 Ang Mo Kio, Industrial Park 2 Singapore 569507 Tel: +65 4866 151

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

单击下面可查看定价,库存,交付和生命周期等信息

>>TE Connectivity(泰科)