
Y5V Dielectric General Specifications






GENERAL DESCRIPTION

Y5V formulations are for general-purpose use in a limited temperature range. They have a wide temperature characteristic of +22% -82% capacitance change over the operating temperature range of -30°C to +85°C. These characteristics make Y5V ideal for decoupling applications within limited temperature range.



PART NUMBER (SEE PAGE 4 FOR COMPLETE PART NUMBER EXPLANATION)






Capacitance Tolerance Z = +80 -20%

Ζ

Failure Rate A = Not Applicable


Α




Т





Temperature Coefficient +20 +10 0 % Δ Capacitance -10 -20 -30 -40 -50 -60 -70 -80 -35 +5 +25 +45 +65 +85 +105 +125 -55 -15 Temperature °C




Insulation Resistance vs. Temperature











The Important Information/Disclaimer is incorporated in the catalog where these specifications came from or available online at www.avx.com/disclaimer/ by reference and should be reviewed in full before placing any order.

Y5V Dielectric Specifications and Test Methods



| Capacitance Within specified tolerance Dissipation Factor ≤ 5.0% for ≥ 50V DC rating Freq.: 1.0 Sisting tion Factor ≤ 5.0% for ≥ 50V DC rating Freq.: 1.0 Insulation Resistance 10,000 MΩ or 500 MΩ - μF, Charge device with rated @ room tem Dielectric Strength No breakdown or visual defects Charge device with 25 Appearance No defects Deflection Variation ≤ ±30% Deflection Dissipation Meets Initial Values (As Above) Deflection Insulation Lattor Perture Sites Deflection Insulation Lattor Lattor Lattor Perture Sites Appearance No breakdown or visual defects Deflection Deflection Insulation Lattor Lattor Deflection Deflection Stresses Appearance Meets Initial Values (As Above) Deflection Insulation Lattor Lattor Lattor Deflection Gaseistance Lattor Lattor Lattor Lattor Insulation Lattor Lattor Lattor Lattor | np/humidity 0% of rated voltage for and discharge current | | | | | | |
|---|---|--|--|--|--|--|--|
| Dissipation Factor $\leq 5.0\%$ for $\geq 50V$ DC rating $\leq 7.0\%$ for 25V DC rating $\leq 9.0\%$ for 16V DC rating $\leq 12.5\%$ for $\leq 10V$ DC rating $\leq 12.5\%$ for $\leq 10V$ DC ratingFreq.: 1.0 Voltage: 1.0 For Cap > 10 μ F, | OVrms ± .2V 0.5Vrms @ 120Hz I voltage for 120 ± 5 sec np/humidity 0% of rated voltage for e and discharge current | | | | | | |
| Dissipation Factor≤ 7.0% for 25V DC rating ≤ 9.0% for 16V DC rating ≤ 9.0% for 16V DC rating ≤ 12.5% for ≤ 10V DC ratingVoltage: 1.0 For Cap > 10 μF, 0Insulation Resistance10,000MΩ or 500MΩ - μF, whichever is lessCharge device with rated @ room ten 0 room tenDielectric StrengthNo breakdown or visual defectsCharge device with 25 1-5 seconds, w/charge limited to 5Resistance to Flexure StressesAppearance Ωissipation FactorNo defects Meets Initial Values (As Above)Deflection 0 and a stressesInsulation | OVrms ± .2V 0.5Vrms @ 120Hz I voltage for 120 ± 5 sec np/humidity 0% of rated voltage for e and discharge current | | | | | | |
| Dielectric Strength Mo breakdown or visual defects Charge device with 25 1-5 seconds, w/charge limited to 5 Resistance to Flexure Stresses Appearance No defects Deflection Test Time: Dissipation Factor Meets Initial Values (As Above) 0 Insulation Resistance ≥ Initial Value x 0.1 90 | np/humidity 0% of rated voltage for and discharge current | | | | | | |
| Dielectric Strength No breakdown or visual defects 1-5 seconds, w/charge limited to 5 Resistance to Flexure Stresses Appearance No defects Deflection Test Time: Dissipation Factor Meets Initial Values (As Above) 0 0 Insulation Resistance ≥ Initial Value x 0.1 90 | e and discharge current | | | | | | |
| Resistance to Flexure Stresses Capacitance Variation ≤ ±30% Test Time: Dissipation Factor Meets Initial Values (As Above) 90 | | | | | | | |
| Resistance to Flexure StressesCapacitance Variation≤ ±30%Test Time: Test Time: Test Time: Test Time: Test Time: Test Time: 0Dissipation FactorMeets Initial Values (As Above)Test Time: 0Insulation Resistance≥ Initial Value x 0.10 | Deflection: 2mm Test Time: 30 seconds | | | | | | |
| Stresses Dissipation Factor Meets Initial Values (As Above) Insulation Resistance ≥ Initial Value x 0.1 90 | | | | | | | |
| Resistance ≥ Initial Value x 0.1 | | | | | | | |
| | | | | | | | |
| | Dip device in eutectic solder at 230 ± 5°C for 5.0 ± 0.5 seconds | | | | | | |
| Appearance No defects, <25% leaching of either end terminal | | | | | | | |
| Capacitance Variation ≤ ±20% | Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 ± 2 hours before measuring electrical properties. | | | | | | |
| Soldar Hast Factor Meets Initial Values (As Above) seconds. Store at room | | | | | | | |
| Insulation Resistance Meets Initial Values (As Above) | ig electrical properties. | | | | | | |
| Dielectric Meets Initial Values (As Above) | | | | | | | |
| Appearance No visual defects Step 1: -30°C ± 2° | 30 ± 3 minutes | | | | | | |
| Capacitance Variation≤ ±20%Step 2: Room Temp | ≤ 3 minutes | | | | | | |
| Dissipation Factor Meets Initial Values (As Above) Step 3: +85°C ± 2° | 30 ± 3 minutes | | | | | | |
| Insulation ResistanceMeets Initial Values (As Above)Step 4: Room Temp | ≤ 3 minutes | | | | | | |
| | Repeat for 5 cycles and measure after 24 ±2 hours at room temperature | | | | | | |
| Appearance No visual defects | | | | | | | |
| | Charge device with twice rated voltage in test chamber set at 85°C ± 2°C for 1000 hours (+48, -0) Remove from test chamber and stabilize at roor temperature for 24 ± 2 hours before measuring | | | | | | |
| Load LifeDissipation Factor≤ Initial Value x 1.5 (See Above)for 1000 ho | | | | | | | |
| Resistance 2 milital value x 0.1 (See Above) temperature for 24 ± 2 h | | | | | | | |
| Dielectric Strength Meets Initial Values (As Above) | | | | | | | |
| Appearance No visual defects | | | | | | | |
| 5% relative humid | Store in a test chamber set at 85°C ± 2°C/ 85% ± 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature and humidity for 24 ± 2 hours before measuring. | | | | | | |
| Humidity Factor | | | | | | | |
| Insulation ≥ Initial Value x 0.1 (See Above) Remove from chambe | | | | | | | |
| Dielectric Meets Initial Values (As Above) | | | | | | | |



The Important Information/Disclaimer is incorporated in the catalog where these specifications came from or available online at www.avx.com/disclaimer/ by reference and should be reviewed in full before placing any order.



PREFERRED SIZES ARE SHADED

| SIZE | | 020 | 01 | 0402 | | | | | 0 | | | 603 | | 0805 | | | | 1206 | | | | 1210 | | | |
|--------------------------|---------|-----------------|-------------|-----------------|-------|------|-----------|-------------|-----------------|-------|----------------|-----------------|-----------------|------|----------------|-----------------|-----------------|------|----------------|-----------------|-----------------|------|---------------|----|--|
| Soldering Reflow O | | / Only | | Ref | low/W | lave | | I | Reflow | /Wave | e | Reflow/Wave | | | | ReflowMfeve | | | | Reflow/Wave | | | | | |
| Packaging All Paper | | All Paper | | | | | All Paper | | | | Paper/Embossed | | | | Paper/Embossed | | | | Paper/Embossed | | | | | | |
| (L) Length mm (in.) | | 0.60 ± | 0.09 | 1.00 ± 0.10 | | | | | 1.60 ± 0.15 | | | | 2.01 ± 0.20 | | | | 3.20 ± 0.20 | | | | 3.20 ± 0.20 | | | | |
| | | (0.024 ± | 0.004) | (0.040 ± 0.004) | | | | | (0.063 ± 0.006) | | | | (0.079 ± 0.008) | | | | (0.126 ± 0.008) | | | | (0.126 ± 0.008) | | | B) | |
| W) Width (in.) | | 0.30 ± | 0.09 | 0.50 ± 0.10 | | | | | .81 : | | | | 1.25 ± 0.20 | | | | 1.60 ± 0.20 | | | | 2.50 ± 0.20 | | | | |
| | | (0.011 ± | 0.004) | (0.020 ± 0.004 | | | | | (0.032 ± 0.006) | | | | (0.049 ± 0.008) | | | | (0.063 ± 0.008) | | | | (0.098 ± 0.008) | | | | |
| (t) Terminal mm (in.) | | 0.15 ± | 0.25 ± 0.15 | | | | | 0.35 ± 0.15 | | | | 0.50 ± 0.25 | | | | 0.50 ± 0.25 | | | | .50 ± 0.25 | | | | | |
| | | (0.006 ± 0.002) | | (0.010 ± 0.006 | | | 006) | | (0.014 ± 0.006) | | | (0.020 ± 0.010) | | | 0) | (0.020 ± 0.010) | | | | (0.020 ± 0.010) | | | | | |
| | WVDC | 6.3 | 10 | 6 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | |
| Сар | 820 | | | | | | | | | | 1 | | | | | | | | | | \mathbf{x} | | -w. | | |
| (pF) | 1000 | | Α | | | | | | | | | | | | | | | | - | Ľ | < | | 5 | < | |
| | 2200 | | Α | | | | | | | | | | | | | | | | | (| 5 | | \mathcal{V} | T | |
| | 4700 | | Α | | | | | | | 1 | 1 | | | | | | | | | 5 | $ \downarrow $ | 1 | | | |
| Сар | 0.010 | Α | Α | | | | | | | | | | | | | | | | | | - | T | | | |
| (µF) | 0.022 | Α | | | | | | | | | | | | | | | | | | | . '. | | | | |
| | 0.047 | Α | | | | С | | | | | | | | | | | | | | | | | | | |
| | 0.10 | | | | С | С | | | | | G | G | | | | K | | | | | | | | | |
| | 0.22 | | | | | | 1 | | | G | | | | | | | | | | | | | | | |
| | 0.33 | | | | | | | | | G | | | | | | | | | | | | | | | |
| | 0.47 | | | | | С | | | | G | G | | | | | | | | | | | | | | |
| | 1.0 | | | С | С | | | | G | G | J | | | N | N | Ν | | М | М | М | | | | Ν | |
| | 2.2 | | | | С | | | | J | | | | | Ν | N | | | | Κ | Q | | | | | |
| | 4.7 | | | | | | | | | | | | Ν | N | N | | | Р | Q | | | N | Ν | | |
| | 10.0 | | | | | | | | | | | | Ν | Р | | | Q | Q | Х | | Х | Q | Q | Ζ | |
| | 22.0 | | | | | | | | | | | | | | | | Q | | | | Х | Z | | | |
| | 47.0 | | | | | | | | | | | | | | | | | | | | | | | | |
| WVDC | | 6.3 | 10 | 6 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | |
| SIZE | 020 | 01 | 0402 | | | | | 0603 | | | 0805 | | | 1 | | 12 | 206 | | 1210 | | | | | | |
| | | | | | | | | | · · · · · | | | | | | | | | | | | | | | | |
| Letter | А | С | E | G | | J | | K | _ | М | | N | | P Q | | X | | Y | Z | | | | | | |
| Max. | 0.33 | 0.56 | 0.71 | 0.90 | | 0.94 | | 1.02 | 1.27 | | 1.40 | | 1.52 | 1 | 1.78 | | 9 | 2.54 | 2.79 | | | | | | |
| Thickness | (0.013) | (0.022) | (0.028) |) (0.035) (0.03 | | 37) | (0.040) | (0. | 050) | (0.05 | 5) (| (0.060) (0 | | 070) | (0.090) | | 0.100) | (0.1 | (0.110) | | | | | | |
| | | PAPER | | | | | | | EMBOSSED | | | | | | | | | | | | | | | | |



单击下面可查看定价,库存,交付和生命周期等信息

>>AVX