


FPL100/100/10-BH1T

Aliases (UFCL100ADB1T00)

KEMET, FPL, Ferrite Materials, Wireless Power Charging



Click here for the 3D model.

Dimensions	
L	100mm +/-2mm
W	100mm +/-2mm
Т	10mm +/-0.2mm

Packaging Specifications			
Packaging	Tray		
Packaging Quantity	2		
Component Weight	490 g		

General Information		
Series	FPL	
Style	Plate	
Features	High frequency range, available in various geometric sizes	
RoHS	Yes	
Qualifications	AEC-Q200	
Initial Permeability	3000 +/-25% (23C)	
Core Loss	345 KW/m3 (23C), 320 KW/m3 (80C), 330 KW/m3 (100C), 370 KW/m3 (120C)	
Effective Saturation Magnetic Flux Density	520 mT (23C), 410 mT (100C)	
Effective Saturation Coercive Force	8.5 A/m (23C)	

Specifications			
Temperature Range	-40/+125°C		
Power Reference	7.2 kW, 11 kW		
Curie Temperature	220C		
Density	4,900 kg/m3		

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

单击下面可查看定价,库存,交付和生命周期等信息

>>KEMET(基美)