SPECIFICATION CONTROL DRAWING

55FA/0514


CABLE, ELECTRIC, FILTER LINE - ELECTROLOSS, OUTER SPACE, COMPONENT WIRE

Date 9-30-13

Revision

В

This specification sheet forms a part of the latest issue of Raychem Specification 55F.



PRIMARY INSULATION - RADIATION-CROSSLINKED, MODIFIED PVDF COLOR - NATURAL PRIMARY JACKET - LOW OUTGASSING, RADIATION-CROSSLINKED, MODIFIED ETFE

TABLE I. CONSTRUCTION DETAILS								
	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	DIAMETER OF STRANDED CONDUCTOR (in.)		FINISHED WIRE			
PART NUMBER 1/					MAXIMUM RESISTANCE AT 20°C	DIAMETER (in.)	MAXIMUM WEIGHT	
			MINIMUM	MAXIMUM	(ohms/1000 ft)	, ,	(lbs/1000 ft.)	
55FA/0514-26-*	26	19 x 38	.018	.020	44.8	.043 ± .002	2.3	
55FA/0514-24-*	24	19 x 36	.023	.025	28.4	.045 ± .002	3.0	
55FA/0514-22-*	22	19 x 34	.029	.032	17.5	.051 ± .003	4.0	
55FA/0514-20-*	20	19 x 32	.037	.040	10.7	.059 ± .003	5.8	

TABLE II. PERFORMANCE DETAILS							
PART NUMBER	BEND TESTING						
	MANDREL DIAMETER (inch) (± 3%)	2	WEIGHT (lb) (± 3%)				
1/	IMMERSION, LIFE CYCLE, AND CROSSLINKING PROOF TEST	COLD BEND	IMMERSION, LIFE CYCLE, AND CROSSLINKING PROOF TEST	COLD BEND			
55FA/0514-26-*	.500	1.00	.500	3.00			
55FA/0514-24-*	.500	2.00	.625	3.00			
55FA/0514-22-*	14-22-* .500		.750	3.00			
55FA/0514-20-*	.750	2.50	1.25	4.00			

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER. AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

Page 1 of 3

Raychem, TE Connectivity, TE connectivity (logo) and TE (logo) are trademarks.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL.

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297

© 2013 Tyco Electronics Corporation,. All rights reserved.

SPECIFICATION CONTROL DRAWING

Page 2 of 3

Revision B 55FA/0514

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level ATTENUATION (INSERTION LOSS): See Table III

BLOCKING: 200 ± 3°C for 6 hours COLOR: Light violet preferred

CONCENTRICITY: Primary Insulation - 50% (minimum); Finished Wire - 70% (minimum)

CROSSLINKING PROOF TEST: 300 ± 3°C for 7 hours

FLAMMABILITY: 3 seconds (maximum); 3 inches (maximum); no flaming of facial tissue HUMIDITY RESISTANCE: Insulation Resistance, 5000 megohms for 1000 ft. (minimum)

IDENTIFICATION AND COLOR STRIPING DURABILITY: 125 cycles (250 strokes) (minimum), 500 g weight

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown

INSULATION ELONGATION AND TENSILE STRENGTH:

Primary Insulation, Filter Layer, and Primary Jacket pulled together

Elongation, 50% (minimum)

Tensile Strength, 3000 lbf/in2 (minimum)

INSULATION FLAWS:

Primary Insulation only,

Spark Test, 1.5 kV (rms) at 60 Hz

4.2 kV (rms) at 3 KHz

Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire,

Spark Test, 3.0 kV (rms) at 60 Hz

5.7 kV (rms) at 3 kHz

Impulse Dielectric Test, 8.0 kV (peak)

INSULATION RESISTANCE: 5000 megohms for 1000 ft. (minimum)

INSULATION THICKNESS:

Primary Insulation, .002 in. (minimum);

Filter Layer, average, .0025 in. (minimum);

Primary Jacket, .0035 in. (minimum) LIFE CYCLE: 200 ± 3°C for 168 hours

LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours

SHRINKAGE: 200 ± 3°C for 6 hours, 0.125 inches (maximum)

SMOKE: 200 ± 2°C, no visible smoke

SURFACE RESISTANCE: 500 megohms-in. (minimum), initial and final readings

THERMAL-SHOCK RESISTANCE: 150 ± 3°C, 0.060 inch (maximum)

THERMAL STABILITY: 180 ± 3°C for 1250 hours

VACUUM STABILITY:

Total Mass Loss (TML), 1.00% (maximum)

Volatile Condensable Material (VCM), 0.10% (maximum)

VOLTAGE WITHSTAND (Post Environmental): 1500 volts (rms), 60 Hz

WRAP TEST: 200 ± 3°C for 6 hours, no cracking

1/ PART NUMBER:

The "*" in the part numbers in Tables I-III shall be replaced by a color code designator, except that violet shall be light violet and designator shall be 7L.

Example: AWG 24, light violet: 55FA/0514-24-7L

AWG 24, light violet with a blue stripe: 55FA/0514-24-7L6

1/ See footer section on page 1

Revision

Page 3 of 3

SCD Number

55FA/0514




TABLE III. ATTENUATION (INSERTION LOSS) +								
PART NUMBER .		PASS BAND (dB/ft.)		TRANSITION BAND (dB/ft.)			STOP BAND (dB/ft.)	
	1.0 MHz	10.0	MHz	100 MHz	500 MHz	1000 MHz	1 to 12 GHz	
	(max)	(min)	(max)	(min)	(min)	(min)	(min)	
55FA/0514-26-*	TBD	TBD	TBD	TBD	TBD	TBD	TBD	
55FA/0514-24-*	.02	.06	0.20	1.3	12	30	30	
55FA/0514-22-*	.02	.06	0.20	1.3	12	30	30	
55FA/0514-20-*	.02	.06	0.20	1.3	12	30	30	

1/ See footer section on page 1

+ THE PRIMARY WIRE OF THIS SPECIFICATION SHEET SHALL MEET THE ATTENUATION REQUIREMENTS SHOWN ABOVE ONLY WHEN USED AS A SINGLE COMPONENT IN A SHIELDED CABLE.

单击下面可查看定价,库存,交付和生命周期等信息

>>TE Connectivity(泰科)