
| SPE | CIFICATION CONTROL DRAWING |
|-------|----------------------------|
| TITLE | |

WIRE, RADIATION-CROSSLINKED, MODIFIED ETFE-INSULATED, HEAVY DUTY, GENERAL PURPOSE, 1000 VOLT 55A0711

Revision C

This specification sheet forms a part of the latest issue of Raychem Specification 55A.

CONDUCTOR - TIN-COATED COPPER



PRIMARY INSULATION - RADIATION-CROSSLINKED, MODIFIED ETFE Primary insulation shall be of a contrasting pigmentation to that of the jacket.

6-17-08

Date

JACKET - RADIATION-CROSSLINKED, MODIFIED ETFE

| TABLE I. CONSTRUCTION DETAILS | | | | | | | |
|-------------------------------|-----------------------|--|---|---------|----------------------------------|-------------------|-------------------|
| PART NUMBER | WIRE SIZE (AWG) | CONDUCTOR STRANDING (number x AWG) | DIAMETER OF STRANDED CONDUCTOR (in.) | | FINISHED WIRE | | |
| | | | | | MAXIMUM RESISTANCE AT 20°C | DIAMETER (in.) | MAXIMUM WEIGHT |
| | | | MINIMUM | MAXIMUM | (ohms/1000 ft.) | | (lbs/1000 ft.) |
| 55A0711-24-* | 24 | 19 x 36 | .023 | .025 | 26.2 | .056 ± .003 | 3.7 |
| 55A0711-22-* | 22 | 19 x 34 | .029 | .031 | 16.2 | .062 ± .003 | 4.9 |
| 55A0711-20-* | 20 | 19 x 32 | .037 | .039 | 9.88 | .070 ± .003 | 5.9 |
| 55A0711-18-* | 18 | 19 x 30 | .046 | .049 | 6.23 | .080 ± .004 | 8.6 |
| 55A0711-16-* | 16 | 19 x 29 | .052 | .055 | 4.81 | .087 ± .004 | 10.5 |
| 55A0711-14-* | 14 | 19 x 27 | .065 | .069 | 3.06 | .103 ± .004 | 15.3 |
| 55A0711-12-* | 12 | 37 x 28 | .084 | .089 | 2.02 | .120 ± .006 | 22.6 |
| 55A0711-10-* | 10 | 37 x 26 | .106 | .113 | 1.26 | .144 ± .006 | 34.6 |
| 55A0711- 8-* | 8 | 133 x 29 | .158 | .173 | .701 | .205 ± .008 | 63.6 |

| | TABLE II. PERFORMANCE DETAILS | | | | | |
|--------------|---|--------------|---|--------------|--|--|
| | BEND TESTING | | | | | |
| PART NUMBER | MANDREL DIAM (inch) (± 3% | | WEIGHT (lb) (± 3%) | | | |
| 1/ | IMMERSION, LIFE CYCLE AND ACCELERATED AGING | COLD BEND | IMMERSION, LIFE CYCLE AND ACCELERATED AGING | COLD BEND | | |
| 55A0711-24-* | 1.00 | 1.25 | 2.00 | 4.00 | | |
| 55A0711-22-* | 1.00 | 1.25 | 2.00 | 4.00 | | |
| 55A0711-20-* | 1.00 | 1.25 | 3.00 | 5.00 | | |
| 55A0711-18-* | 1.00 | 1.25 | 3.00 | 5.00 | | |
| 55A0711-16-* | 1.25 | 1.50 | 3.50 | 5.50 | | |
| 55A0711-14-* | 1.25 | 1.50 | 3.50 | 5.50 | | |
| 55A0711-12-* | 2.00 | 3.00 | 4.00 | 6.00 | | |
| 55A0711-10-* | 2.00 | 3.00 | 4.00 | 6.00 | | |
| 55A0711- 8-* | 4.00 | 5.00 | 4.00 | 8.00 | | |

| | Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer. | | | | | |
|--------|---|--|-------------|---|--|--|
| | 1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER. AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER. | | | | | |
| | | The TE logo, Tyco Electronics and Raychem are trademarks. | | Raychem Wire & Cable | | |
| Page 1 | Page 1 of 2 | DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL. | ₹ Tyco | 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297 | | |
| | r uge r or z | THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID. | Electronics | | | |

© 2008 Tyco Electronics Corporation. All rights reserved.

Revision

С

SCD Number

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C Maximum continuous conductor temperature VOLTAGE RATING: 1000 volts (rms) at sea level ACCELERATED AGING (CROSSLINKING PROOF): 300 ± 3°C for 7 hours BLOCKING: 200 ± 3°C for 24 hours COLOR: White preferred CONCENTRICITY: 70% (minimum) FLAMMABILITY: Procedure 1, 3 seconds (maximum); 3 inches (maximum); no flaming of facial tissue HUMIDITY RESISTANCE: Insulation Resistance, 5000 megohms for 1000 ft. (minimum), AWG 24 - 10 3000 megohms for 1000 ft. (minimum), AWG 8 IDENTIFICATION AND COLOR STRIPING DURABILITY: 125 cycles (250 strokes) (minimum), 500 g weight IMMERSION: Diameter increase 5% (maximum): no cracking, no dielectric breakdown INSULATION ELONGATION AND TENSILE STRENGTH: Total Insulation (primary insulation and jacket) Elongation, 50% (minimum) Tensile strength, 5000 lbf/in² (minimum) **INSULATION FLAWS:** Primary Insulation, Spark Test, 1.5 kV (rms) Impulse Dielectric Test, 6.0 kV (peak) Finished Wire, Spark Test, 3.0 kV (rms) Impulse Dielectric Test, 8.0 kV (peak) INSULATION RESISTANCE: 5000 megohms for 1000 ft. (minimum), AWG 24 - 10 3000 megohms for 1000 ft. (minimum), AWG 8 INSULATION THICKNESS: 0.014 in. (minimum) for total insulation LIFE CYCLE: 200 ± 3°C for 500 hours LOW TEMPERATURE-COLD BEND: -65 ± 3°C for 4 hours SHRINKAGE: 200 ± 3°C for 6 hours, 0.125 in. (maximum) in 12 inches SMOKE TEST: 200 ± 2°C, no visible smoke SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings THERMAL SHOCK RESISTANCE: 150 ± 3°C 0.060 in. (maximum) for AWG 24 - 12 0.100 in. (maximum) for AWG 10 - 8 VOLTAGE WITHSTAND TEST (Post Environmental): 2500 volts (rms), 60 Hz

PART NUMBER: The "*" in the part numbers on page 1 shall be replaced by a color code designator. <u>1</u>/ Example: AWG 22, white; 55A0711-22-9 AWG 22, white with a black stripe; 55A0711-22-90

1/ See footer section on page 1

单击下面可查看定价,库存,交付和生命周期等信息

>>TE Connectivity(泰科)