81A1122

TITLE

TWO CONDUCTOR CABLE, SHIELDED, JACKETED, FLEXIBLE


Date

1-24-96

evision

Д

This specification sheet forms a part of the latest issue of Raychem Specification 80.



CABLE CONSTRUCTION DETAILS							
PART NUMBER	CONDUCTOR SIZE (AWG)	SHIELD SIZE (AWG)	JACKET THICKNESS (inches)		OUTSIDE DIAMETER (inches)		MAXIMUM WEIGHT (lbs/1000 ft)
			MINIMUM	NOMINAL	NOMINAL	MAXIMUM	
81A1122-26-*	26	38	.006	.009	.097	.102	8.0
81A1122-24-*	24	38	.006	.009	.107	.112	9.9
81A1122-22-*	22	38	.007	.010	.121	.127	13.0
81A1122-20-*	20	38	.007	.010	.139	.146	17.5
81A1122-18-*	18	38	.007	.011	.161	.169	24.3
81A1122-16-*	16	38	.008	.012	.177	.186	29.6
81A1122-14-*	14	38	.009	.013	.209	.219	41.9

## CABLE RATINGS AND ADDITIONAL REQUIREMENTS

**TEMPERATURE RATING: 150°C** 

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms)
BLOCKING: 150°C ± 3°C for 6 hours

CROSSLINKING PROOF TEST: 300 ± 3°C for 1 hour DIELECTRIC WITHSTAND: 1500 volts (rms), 60 Hz FLAMMABILITY: Procedure 1, 3 seconds (maximum);

3 inch (maximum)

JACKET COLOR: White preferred

JACKET ELONGATION AND TENSILE STRENGTH:

Elongation, 100% (minimum)

Tensile Strength, 3000 lbf/in² (minimum)

JACKET FLAWS:

Spark Test, 1500 volts (rms), 60 Hz, 100% test or Impulse Dielectric Test, 6.0 kV (peak), 100% test

LOW TEMPERATURE-COLD BEND: -65 ± 3°C SECANT MODULUS: 4.0 X 104 lbf/in² (maximum),

2% strain, 2 in. Jaw separation, 0.2 in./minute, procedural reference ASTM D 882

SHIELD COVERAGE: 85% (minimum)

**VOLTAGE WITHSTAND (POST ENVIRONMENTAL):** 

1000 volts (rms), 60 Hz, 1 minute

## PART NUMBER

The """ in the part numbers above shall be replaced by color code designators with a slash separating the component wire colors and a dash separating the component wire colors from the jacket color.

Example: AWG 14, white and black component wires; white jacket: 81A1122-14-9/0-9

COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL.

Page 1 of 1

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.

Raychem

Raychem Corporation 300 Constitution Drive, Menlo Park, California 94025 1-800-2 Raychem Fax: 1-415-381-6297

## 单击下面可查看定价,库存,交付和生命周期等信息

## >>TE Connectivity(泰科)