



Raychem HRHF and HRSR High Shrink Ratio Heat Shrinkable Tubing

108-120059
Formerly RW-2013

High-ratio (HR) heat-shrinkable tubing, with expansion ratios as high as 5.1 to 1, is designed to accommodate large size differences between cables and cable connectors and back-shells, thus simplifying repair of damaged cable. High-ratio tubing is available in semirigid flame-retardant (SR) or high-flex flame-retardant (HF) material and with or without factory-applied sealants and adhesives. The waterproofing sealant provides environmental sealing and is watertight in wet and corrosive locations. The thermoplastic adhesive coating offers excellent strain relief and environmental sealing.

RoHS and REACH compliant

Continuous Operating Temperature -55°C to 110°C (-67°F to 230°F)

THIS IS A CLASS 1 DOCUMENT WHICH IS NONCONFIDENTIAL.

The information contained within this document is the property of TE Connectivity. It is supplied in confidence and the commercial security of the contents must be maintained. It must not be used for any purpose other than that for which it is supplied nor may any information contained in it be disclosed to unauthorized persons. It must not be reproduced in whole or in part without obtaining written permission from TE Connectivity (TE).

While TE has made every reasonable effort to ensure the accuracy of the information in this catalog, TE does not guarantee that it is error-free, nor does TE make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. TE reserves the right to make any adjustments to the information contained herein at any time without notice. TE expressly disclaims all implied warranties regarding the information contained herein, including, but not limited to, any implied warranties of merchantability or fitness for a particular purpose. The dimensions in this catalog are for reference purposes only and are subject to change without notice. Specifications are subject to change without notice. Consult TE for the latest dimensions and design specifications.

*Trademark. TE Connectivity, TE connectivity (logo), and TE (logo) are trademarks. Other logos, product and/or company names may be trademarks of their respective owners.



Table of Contents

1. SCOPE 3

 1.1. HRSR..... 3

 1.2. HRHF.....3

2. APPLICABLE DOCUMENTS 3

 2.1. AMERICAN SOCIETY FOR TESTING AND MATERIAL 3

 2.2. INTERNATIONAL ORGANIZATION FOR STANDARDIZATION.....3

 2.3. MILITARY DOCUMENTS.....4

3. REQUIEMENTS 4

 3.1 MATERIALS4

 3.2 PROPERTIES 4

4. QUALITY ASSURANCE PROVISIONS 4

 4.1 CLASSIFICATION OF TESTS 4

 4.1.1 Qualification Tests 4

 4.1.2 Acceptance Tests4

 4.2 SAMPLING INSTRUCTIONS4

 4.2.1 Qualification Test Samples4

 4.2.2 Acceptance Test Samples4

 4.2.3 Lot Formation 5

 4.3 TEST PROCEDURES 5

 4.3.1 Dimensions and Longitudinal Change 5

 4.3.2 Tensile Strength and Ultimate Elongation 5

 4.4 REJECTION AND RETEST5

5. PREPARATION FOR DELIVERY 5

 5.1 FORM 5

 5.2 PACKAGING 5

 5.3 MARKING 5

APPENDIX 6

TABLE 1 REQUIREMENTS..... 6



1. SCOPE

This specification covers the requirements for three types of electrically insulating, extruded tubing whose diameter will reduce to a predetermined size upon the application of heat in excess of 121°C (250°F). They are suitable for use with Hot Melt Adhesive /97 or Sealant /226.

1.1. HRSR.

HRSR tubing is a semi rigid, flame retardant, cross-linked modified polyolefin. The standard color is black and can be supplied with a Sealant or Hot Melt Adhesive.

1.2. HRHF

HRHF tubing is a highly flexible, flame retardant cross-linked modified polyolefin. The standard color is black (and clear for non-flame-retardant material) and can be supplied with a Sealant or Hot Melt Adhesive.

2. APPLICABLE DOCUMENTS

This specification takes precedence over documents referenced herein. Unless otherwise specified, the latest issue of referenced documents apply. The following documents form a part of this specification to the extent specified herein.

2.1. AMERICAN SOCIETY FOR TESTING AND MATERIAL (ASTM)

ASTM D 570	Standard Test Method for Water Absorption
ASTM D 638	Standard Test Methods for Tensile Properties of Plastics
ASTM D 792	Standard Test Method for Specific Gravity (Relative Density) and Density of Plastics by Displacement
ASTM D 876	Standard Test Methods for Non-Rigid Vinyl Chloride Polymer Tubing Used for Electrical Insulation
ASTM D 882	Standard Test Methods for Tensile Properties of Thin Plastic Sheeting
ASTM D 2671	Standard Test Methods for Heat-Shrinkable Tubing for Electrical Use

(Copies of ASTM publications may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103 or via the ASTM website at <http://www.astm.org>).

2.2. INTERNATIONAL ORGANIZATION FOR STANDARDIZATION (ISO)

ISO 846 Method B	Plastics – Evaluation of the Action of Microorganisms
------------------	---

(Copies of ISO publications may be obtained from the International Organization for Standardization, 1, rue de Varembé, CH-1211 Geneva 20, Switzerland or via the ISO website at <http://www.iso.ch/iso/en/ISOOnline.frontpage>)



2.3. MILITARY DOCUMENTS

MIL-H-5606	Hydraulic Fluid Petroleum Base, Aircraft, Missile and Ordnance
MIL-PRF-7808	Lubricating Oil
MIL-A-8243	De-icing Fluids
MIL-L-23699	Lubricating Oil
MIL-DTL-83133	Turbine Fuel, Aviation, Grade JP-8
AMSDDL23053™	Insulating Tubing, Electrical, Heat Shrinkable, General Specification
A-A-694	5% NaCl

(Copies of Military documents are available online at <http://quicksearch.dla.mil> or <https://www.sae.org/standards/>)

3. REQUIREMENTS

3.1. Material

The tubing shall be fabricated from thermally stabilized, modified polyolefin and shall be irradiation cross-linked. It shall be homogeneous and essentially free from flaws, defects, pinholes, bubbles, seams, cracks and inclusions.

3.2. Properties

The tubing shall meet the requirements of Tables 1 and 2.

4. QUALITY ASSURANCE PROVISIONS

4.1. CLASSIFICATION OF TESTS

4.1.1. Qualification Tests

Qualification tests are those performed on the tubing submitted for qualification as a satisfactory product and shall consist of all the tests listed in this specification.

4.1.2. Acceptance Tests

Production routine tests shall be carried out on every batch, unless otherwise specified and shall consist of the following: dimensions, longitudinal change, tensile strength, ultimate elongation, heat shock, low temperature flexibility and flammability. Flammability is not applicable clear tubing.

4.2. SAMPLING INSTRUCTIONS

4.2.1. Qualification Test Sample

Qualification test samples shall consist of 50 feet (15m) of tubing. Qualification of any size qualifies all sizes. The color shall be black.

4.2.2. Acceptance Test Sample

Production routine test samples shall consist of a sufficient length to perform all the tests in 4.1.2 selected at random from each batch.

HRHF and HRSR Specification



4.2.3. Lot Formation

A batch shall consist of all tubing of the same size, from the same production run and offered for inspection at the same time. Physical property tests performed at this time qualify subsequent tubing lots produced from the same compound batch.

4.3. TEST PROCEDURES

Unless otherwise specified the tubing shall be recovered in a forced air circulating oven for 10 minutes at $150 \pm 2^\circ\text{C}$. All tests shall be performed without the adhesive. Uncoated samples are available upon request.

4.3.1. Dimensions and Longitudinal Change

The test method shall be as specified in ASTM D 2671.

The length and inside diameter of three 250 mm long specimens of expanded tubing shall be measured. The specimens shall be recovered and the length and inside diameter of each shall be measured. The longitudinal change shall be expressed as a percentage of the original length. The minimum and maximum recovered wall thicknesses shall be determined.

4.3.2. Tensile Strength and Ultimate Elongation

The test method shall be as specified in ASTM D 638.

For tubing of recovered inside diameter greater than 6 mm, five Type IV dumbbell specimens shall be tested. For tubing of recovered inside diameter less than or equal to 6 mm, five tubular specimens 150 mm long shall be tested. Rate of jaw separation shall be 500 ± 10 mm per minute.

The test shall be carried out at a temperature of $23 \pm 2^\circ\text{C}$.

4.4. REJECTION AND RETEST

Failure of any sample of tubing to conform to any one of the requirements of this specification shall be cause for rejection of the lot represented. Tubing which has been rejected may be replaced or reworked to correct the defects and resubmitted for acceptance. Before resubmitting, full particulars concerning previous rejection and action taken to correct the defects shall be furnished to Quality.

5. PREPARATION FOR DELIVERY

5.1. FORM

The tubing shall be supplied in cut lengths unless otherwise specified.

5.2. PACKAGING

Packaging shall be in accordance with good commercial practice.

5.3. MARKING

Each container of tubing shall be permanently and legibly marked with the size, quantity, manufacturer's identification and batch number.



APPENDIX

PROPERTY	UNIT	HRHF	HRSR	TEST METHOD
PHYSICAL Dimensions	mm (<i>in.</i>)	In Accordance with HRHF AND HRSR SCD		Section 4.3.1 ASTM D 2671
Longitudinal Change	Percent	+1, - 10	+1, -10	Section 4.3.1 ASTM D 2671
Tensile Strength	MPa	8.4 Min.	8.4 Min.	Section 4.3.2 ASTM D 638
Ultimate Elongation	Percent	200 Min.	200 Min.	Section 4.3.2 ASTM D 638
Secant Modulus (Expanded)	MPa	120 Max.	220 Max.	ASTM D 882
Specific Gravity		1.4 Max.	1.5 Max.	ASTM D 792
Low Temperature Flexibility 4 hours at -55 ± 2°C		No cracking	No cracking	AMSDTL23053™
Heat Shock 4 hours at 225 ± 3°C		No dripping, flowing or cracking	No dripping, flowing or cracking	AMSDTL23053™
Heat Resistance 168 hrs at 175 ± 2°C for HRHF-BK/HRSR 168 hrs at 150 ± 2°C for / HRHF- CL Followed by tests for Tensile Strength Ultimate Elongation	MPa Percent	7.0 Min. 100 Min.	7.0 Min. 100 Min.	ASTM D 638 ASTM D 638
ELECTRICAL				ASTM D 2671
Dielectric Strength	KV/mm	7.9 Min.	7.9 Min.	*Note 1
Volume Resistivity	Ohm-cm	1 x 10 ¹³ Min.	1 x 10 ¹³ Min.	ASTM D 876

Requirements continued on the next page.

TABLE 1 CONTINUED

HRHF and HRSR Specification



REQUIREMENTS

PROPERTY	UNIT	HRHF	HRSR	TEST METHOD
CHEMICAL Copper Mirror Corrosion 16 hours at 120 ± 2°C		No removal of copper	No removal of copper	AMSDTL23053™
Copper Contact Corrosion 16 hours at 120 ± 2°C		No pitting or blackening of copper	No pitting or blackening of copper	SAE-AMS-DTL-23053
Flammability	Seconds	Procedure B 15 Max. *Note 3	Procedure C 60 Max.	AMSDTL23053™ ASTM D2671
Fungus Resistance Followed by tests for Tensile Strength Ultimate Elongation Dielectric Strength	MPa Percent KV/mm	8.4 Min. 200 Min. 7.9 Min.	8.4 Min. 200 Min. 7.9 Min.	ISO 846 Method B ASTM D 638 ASTM D 638 ASTM D 2671
Water Absorption 24 hours at 23 ± 2°C	Percent	0.5 Max.	0.5 Max.	ASTM D 570
Fluid Resistance 24 hours at 23 ± 2°C JP-8 Fuel (MIL-DTL-83133) Hydraulic Fluid (MIL-H-5606) De-icing Fluid (MIL-A-8243) Lube Oil (MIL-PRF-7808) Lube Oil (MIL-L-23699) 5% NaCl (A-A-694) Followed by tests for Tensile Strength Ultimate Elongation Dielectric Strength	MPa Percent KV/mm	5.2 Min. 100 Min. 7.9 Min.	5.2 Min. 100 Min. 7.9 Min.	AMSDTL23053™ . ASTM D 638 ASTM D 638 ASTM D 2671 *Note 2

***Note 1** Recover specimens on the metal mandrels for 10 minutes, minimum, at 200 ± 3°C or until the tubing is completely recovered on the mandrels.

***Note 2** For dielectric strength, immerse the recovered specimens in the fluids for 24 hours at 50 ± 2°C. After drying, place the specimens over closest fitting metal mandrels.

***Note 3** N/A for HRHF-CL, which is non-flame retardant.

单击下面可查看定价，库存，交付和生命周期等信息

[>>TE Connectivity\(泰科\)](#)