SPECIFICATION CONTROL DRAWING

CHEMINAX

.0250

.0515

+.002

- .001

.035

.120

.124

141

.157

77 OHM, AWG 24, 19 STRANDS OF AWG 36 DATA BUS CABLE, MIL-STD-1553 Date: 8-8-18

Revision:

7724Y3664

F

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

CONSTRUCTION DETAILS

ELECTRICAL CHARACTERISTICS

DIMENSIONS ARE NOMINAL VALUES IN INCHES, UNLESS OTHERWISE DESIGNATED.

CHARACTERISTIC IMPEDANCE 77 ± 5 ohms, Method C at 1 MHz
MUTUAL CAPACITANCE 30.0 pF/ft. (maximum)

ATTENUATION

1.4 dB/100 ft. (maximum) at 1 MHz

CONDUCTORS

AWG 24, 19 Strands of AWG 36, Silver-Coated High-Strength Copper Alloy

Radiation-Crosslinked,

Radiation-Crosslinked,

Colors - Light Blue/White

ADDITIONAL REQUIREMENTS

COMPONENT WIRE PRIOR TO CABLING (Test procedures per SAE AS22759)

CONDUCTOR RESISTANCE 26.5 ohms/1000 ft. (nominal)

CROSSLINKING PROOF TEST 300 ± 3°C for 1 hour, .500 inch mandrel,

.375 lb, 2.5 kV dielectric test

INSULATION (DIELECTRIC)

ELONGATION 50% (minimum)
TENSILE STRENGTH 5000 lbf/in² (minimum)

INSULATION FLAWS

SPARK TEST 3.0 kV (rms)
IMPULSE TEST 8.0 kV (peak)

INSULATION RESISTANCE 5000 megohms for 1000 ft. (minimum)

LOW TEMPERATURE-COLD BEND -65 ± 3°C for 4 hours, .500 inch mandrel,

1.00 lb, 2.5 kV dielectric test

SHRINKAGE $200 \pm 3^{\circ}$ C for 1 hour.

.125 inch (maximum) in 12 inches

1st SHIELD

WRAP

DIELECTRICS

FILLERS

Modified ETFE

Modified ETFE

AWG 38, Tin-Coated Copper

Separator Tape

Tin-Coated Copper

Radiation-Crosslinked,

Modified ETFE

2nd SHIELD

AWG 38

JACKET

FINISHED CABLE

(Test procedures per NEMA WC 27500, unless otherwise specified)

BLOCKING 200°C for 6 hours

CABLE LAY LENGTH .75 inch (minimum), 1.25 inches (maximum) CROSSLINKED VERIFICATION $300 \pm 5^{\circ}$ C for 6 hours, 6.00 inch mandrel FLAMMABILITY 3 seconds (maximum), 3 inches (maximum);

(Method B of Spec 1200) no flaming of facial tissue

JACKET

ELONGATION 50% (minimum)
TENSILE STRENGTH 5000 lbf/in² (minimum)

JACKET FLAWS

 SPARK TEST
 1.0 kV (rms)

 IMPULSE TEST
 6.0 kV (peak)

 JACKET THICKNESS
 .008 inch (nominal)

LOW TEMPERATURE-COLD BEND -55 ± 5°C for 4 hours, 6.00 inch mandrel

SHIELD COVERAGE (each) 85% (minimum)

VOLTAGE WITHSTAND 1000 volts (rms) (minimum)

(DIELECTRIC)

WRAP .001 inch thick (nominal), 25% overlap (minimum)

CABLE IDENTIFICATION: Outer jacket shall be marked in contrasting color

at 12 inch (nominal) intervals between marks follows:

7724Y3664-* RAYCHEM Where * = applicable jacket color

WEIGHT 22.4 lbs/1000 ft. (nominal)

with MIL-STD-681. Unless otherwise specified, outer jacket color will be white designated by a "-9" appended to the part number, e.g. 7724Y3664-9.

Designate outer jacket color with a dash number in accordance

Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order

ENGINEERING REFERENCE

TEMPERATURE RATING 150°C (maximum)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. TE Connectivity also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

Page 1 of 1

Cheminax, Raychem, TE Connectivity, and TE connectivity (logo) are trademarks.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, California 94063-3800 Phone: 1-800-522-6752 Fax: 1-650-361-6297

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.

© 2012-2018 TE Connectivity Ltd. family of companies. All Rights Reserved.

单击下面可查看定价,库存,交付和生命周期等信息

>>TE Connectivity(泰科)